

# Technical Datasheet

## Structalit® 5720



### Product Description

Modified epoxy | 1 part | solvent-free | heat-curing

- ▶ Glob top
- ▶ Fill for "Frame and Fill"
- ▶ Electrics
- ▶ Electronics
- ▶ Very good flowability
- ▶ High glass transition temperature
- ▶ No bleeding
- ▶ Very low ionic content (<10ppm)
- ▶ Suitable for semiconductors

### Curing Properties

This adhesive must be cured with heat. Typical curing temperatures are listed in the table below.

Temperatures	Time
120°C	45 min
150°C	15 min

The heat cure times are only provided as a guideline. They are derived from curing a 2g adhesive sample without affixed substrates in a laboratory environment. Actual cure times can vary based on part size, configuration, adhesive volume, temperature control, and the time required for the component substrates to attain oven temperature.

The final bond strength of the adhesive is achieved no sooner than 24 h after the bonded components are removed from the oven.

# Technical Datasheet

## Structalit® 5720



### Technical Data

Resin	Epoxy
Appearance	Black
Filler	Quartz
Filler - weight [%]	50
Particle size D95 [µm]	40

### Uncured Material

Viscosity [mPas] (Kinexus Rheometer, 25 °C, 5s <sup>-1</sup> ) <i>PE-Norm 064</i>	10,000 – 15,000
Thixotropic index [1/10] <i>PE-Norm 064</i>	1.4 – 1.7
Density [g/cm <sup>3</sup> ] <i>PE-Norm 004</i>	1.4 – 1.6
Flash point [°C] <i>PE-Norm 050</i>	>100

### Cured Material

Hardness shore D <i>150°C, 1h</i> <i>PE-Norm 006</i>	70 – 90
Temperature resistance [°C] <i>PE-Norm 059</i>	-40 – 200
Shrinkage [%] <i>150°C, 1h</i> <i>PE-Norm 031</i>	<1
Water absorption [%] <i>150°C, 1h</i> <i>PE-Norm 016</i>	<1

Glass transition temperature - DSC [°C] <i>150°C, 1h</i> <i>PE-Norm 009</i>	150 – 180
Coefficient of thermal expansion [ppm/K] below Tg <i>150°C, 1h</i> <i>PE-Norm 017</i>	<40
Coefficient of thermal expansion [ppm/K] above Tg <i>150°C, 1h</i> <i>PE-Norm 017</i>	100 – 150

Thermal conductivity [W/m*K] <i>150°C, 1h</i> <i>PE-Norm 062</i>	0.2 – 0.4
Dielectric constant [10kHz] <i>150°C, 1h</i> <i>IEC 62631-2-1</i>	1 – 3
Dielectric strength [kV/mm] <i>150°C, 1h</i> <i>DIN EN 60243</i>	18 – 22

# Technical Datasheet

## Structalit® 5720



Young's modulus – Tensile test [MPa] <i>150°C, 1h</i> <i>PE-Norm 056</i>	6,500 – 8,000
Tensile strength [MPa] <i>150°C, 1h</i> <i>PE-Norm 014</i>	24 – 30
Elongation at break [%] <i>150°C, 1h</i> <i>PE-Norm 014</i>	<1

### Transport/Storage/Shelf Life

Package type	Transport	Storage	Shelf life*
Syringe/Cartridge	-20°C	-20°C	At delivery min. 3 months max. 6 months
Other packages			

**\*Store in original, unopened containers!**

# Technical Datasheet

## Structalit® 5720



### Instructions for use

#### Surface preparation

The surfaces to be bonded should be free of dust, oil, grease, mold release, or other contaminants in order to obtain an optimal and reproducible bond. For cleaning we recommend the cleaner IP® from Panacol, or a solution of Isopropyl Alcohol at 90% or higher concentration. Substrates with low surface energy (e.g. polyethylene, polypropylene) must be pretreated in order to achieve sufficient adhesion.

#### Application

Our products are supplied ready to use. Depending on packaging they can be applied by hand directly from the container or by using compatible dispensing systems and automation. Many commercially available valve and controller options are available to ensure accurate and consistent adhesive dispensing. For assistance with dispensing and curing questions, please contact our Applications Engineering department. To obtain best results, the adhesive and substrates to be bonded may not be cold and should be allowed to warm to room temperature prior to processing. For safety information refer to our Material Safety Data Sheet (MSDS).

#### Storage

Store uncured product in its original, closed container in a dry location. Any material removed from the original container must not be returned to the container as it could be contaminated. Panacol cannot assume responsibility for products that were improperly stored, contaminated, or repackaged into other containers.

#### Handling and Clean-up

For safe handling information, consult this product's Material Safety Data Sheet (MSDS) prior to use. Uncured material may be wiped away from surfaces with organic solvents. Do not use solvents to remove material from eyes or skin!

# Technical Datasheet

## Structalit® 5720



### Disclaimer

The product is free of heavy metals, PFOS and Phthalates and is conform to the current EU-Directive RoHS.

**THE VALUES NOTED IN THIS TECHNICAL DATA SHEET ARE TYPICAL PROPERTIES AND ARE NOT MEANT TO BE USED AS PRODUCT SPECIFICATIONS.**

The information contained in this data sheet is believed to be accurate and is provided for information only. Panacol makes no representation or warranties of any kind concerning this information. It is the user's responsibility to determine the suitability of this product for any intended use. Panacol does not assume responsibility for test or performance results obtained by the user. The user assumes all risk and liability connected with the use of this product.

The user should adopt such precautions and use guidelines as may be advisable for the protection of property and persons against any hazards that may be involved in this product's handling or use. Panacol specifically disclaims any liability for consequential or incidental damages of any kind arising from the handling or use of this product. The information contained in this Technical Data Sheet offers no assurance that the product use, application, or process will not infringe on existing patents or licenses of others. Nothing in this Technical Data Sheet transfers or grants license for the use of any patents, trade secrets, intellectual property, or confidential information that is the property of Panacol.

Except as otherwise noted, all trademarks in this document (identified as ®) are the property of Panacol.

### Contact

Panacol-Elosol GmbH  
Stierstädter Straße 4  
61449 Steinbach  
Germany  
Phone: +49 6171 6202-0  
Mail: [info@panacol.de](mailto:info@panacol.de)  
[www.panacol.com](http://www.panacol.com)

Panacol-USA, Inc.  
142 Industrial Lane  
Torrington CT 06790  
USA  
Phone: +1 860-738-7449  
Mail: [info@panacol-usa.com](mailto:info@panacol-usa.com)  
[www.panacol-usa.com](http://www.panacol-usa.com)

Panacol-Korea Co., Ltd.  
#707, Kranz Techno,  
388 Dunchon-daero  
Junwon-gu, Seongnam  
Gyeonggi-do, 13403 KOREA  
Phone: +82 31 749 1701  
Mail: [info@panacol-korea.com](mailto:info@panacol-korea.com)  
[www.panacol-korea.com](http://www.panacol-korea.com)

Eleco Panacol – EFD  
125, av Louis Roche  
Z.A. des Basses Noëls  
92238 Gennevilliers Cdx FRANCE  
Tél.: +33 (0)1 47 92 41 80  
Mail: [eleco@eleco-panacol.fr](mailto:eleco@eleco-panacol.fr)  
[www.eleco-panacol.fr](http://www.eleco-panacol.fr)